



JOSE MESTRE, S.A.

EXCLUSIVAS - ENVASES - ARTICULOS DE ORTOPEDIA

DOMICILIO SOCIAL Y OFICINAS:
Providencia, 70 - 08024 Barcelona
Teléfono: 932857040* - Fax: 932841109

N.I.F.: ES-A59943571
www.josemestre.com

DELEGACION CENTRO:
Av. Pedro Diez, 27 - 28019 Madrid
Teléfono: 914720985 - Fax: 914720988

TECHNICAL DATA FILE "EVOLUTION" BOTTLE

PHYSICAL AND CHEMICAL PROPERTIES

BOTTLE

HDPE BL2571N

Fabricated with **HDPE BL2571N**, which satisfies the requirements established by most of the countries for polymer materials used in fabrication of products destined to food contact.

No heavy metals like cadmium, chrome (hexavalent), plumb and mercury are used or incorporated in the product fabrication process.

* Physical properties

- MFR (190 °C/ 2.16 kg)	0.2 g/10 min	according ISO 1133
- MFR (190 °C/ 5 kg)	0.9 g/10 min	according ISO 1133
- MFR (190 °C/ 21.6 kg)	19 g/10 min	according ISO 1133
- Density	957 kg/m ³	according ISO 1183

DROPPER

LDPE Lupolen 1840 H

Complies with the 177.1520 FDA regulation and most of the Europe applicable food contact regulation.

* Physical properties

- MFR (190 °C/2.16 kg)	1.6 g/10 min	according ISO 1133
- Density	0.919 g/cm ³	according ISO 1183

Revision date: 15/03/2005



JOSE MESTRE, S.A.

EXCLUSIVAS - ENVASES - ARTICULOS DE ORTOPEDIA

DOMICILIO SOCIAL Y OFICINAS:
Providencia, 70 - 08024 Barcelona
Teléfono: 932857040* - Fax: 932841109
N.I.F.: ES-A59943571
www.josemestre.com

DELEGACION CENTRO:
Av. Pedro Diez, 27 - 28019 Madrid
Teléfono: 914720985 - Fax: 914720988

CAP

PP Moplen HP501H

Complies with the 177.1520 FDA regulation and most of the Europe applicable food contact regulation.

* Physical properties

- MFR (230 °C/2.16 kg)	2.1 g/10 min	according ISO 1133
- MFR (190 °C/5 kg)	3.7 g/10 min	according ISO 1133
- Density	0.9 g/cm ³	according ISO 1183

DOSAGE PUMP

PP/PE/Stainless steel/Acetalic resin

The containers have been manufactured in compliance with the requirements of the Spanish Royal Pharmacopoeia and to minimise effects on particles, impurities and/or aesthetic defects, to be ready for use.

ROSER HUARTE PRATS
Technical Director
Bar Assn. No. 14413-C

Revision date: 15/03/2005