

DOMICILIO SOCIAL Y OFICINAS: Providència, 70 - 08024 Barcelona Teléfono: 932 857 040* - Fax: 932 841 109

DELEGACION CENTRO:

Av. Pedro Díez, 27 - 28019 Madrid Teléfono: 914 720 985 - Fax: 914 720 988

Web: http://www.josemestre.com N.I.F.: ES-A59943571













CONDAL

Protecpie

ROCADERM

TECHNICAL DATA FILE WHITE SQUARED JAR 350ML WITH WHITE **SEAL CAP**

PHYSICAL AND CHEMICAL PROPERTIES

JAR

35060E HDPE

It can be easily processed on standard polyethylene blow molding equipments, using melt temperatures between 170°C and 200°C. It combines a high impact resistance with a high environmental stress crack resistance (ESCR) and a good stiffness.

Especially suitable for the bottles production.

The material complies with the applicable regulations throughout materials which can be in contact with food and for pharmaceutical and medical industry.

White pigment

Cylindrical granule preparation which permits a precise dosage and a good color distribution on the final product. Maximum dispersibility and solidity. Environmentally friendly due to its exemption of Cd, heavy metals and diarylides. Suitable for being in contact with food.

ADHESIVE DISK 55 x 47,5mm **HDPE**

CAP PP

> All the materials fulfils with the standards established by the FDA, BGW, BGA, DM. 21/03/73, CONEG, EC 90/128, EC 2002/72

> According the 3rt article from the European Regulation 1935/2004, the final user of the product must determinate if the product is technically adequate for its planed use and the safe use of this one.

> > ROSER HUARTE PRATS **Technical Director** Biologist bar assn. No. 14413-C

Revision date: 15/11/2012